




**UPEC**  
CSTB  
U2SP2E1C0  
14/302



**Composition** 100% Polyamide  
*Pile material* 100% Nylon  
*Polmaterial* 100% Polyamid  
*Poolmateriaal* 100% Polyamide  
*Composición* 100% Poliamida  
*Composizione* 100% Poliammide  
*Sklad runa* 100% Poliamid

**Poids de velours / Pile weight /**  
*Poleinsatzgewicht / Poolinsetzmasse /*  
*Peso fibra / Peso felpa / Gramatura* **1 000 g/m²**

**Poids total - NF ISO 8543 / Total weight /**  
*Gesamtgewicht / Totaal gewicht /*  
*Peso total / Peso totale / Masa całkowita* **1 995 g/m²**

**Épaisseur totale - NF ISO 1765 /**  
*Total thickness / Gesamtdicke*  
*/ Totale massa / Altura total /*  
*Spessore totale / Wysokość całkowita* **6,8 mm**

**Hauteur du velours - NF ISO 1766 /**  
*Pile height / Polhöhe / Poolhoogte /*  
*Altura fibra / Spessore felpa / Wysokość runa* **4,8 mm**

**Envers / Backing /**  
*Rückenausstattung / Rug /*  
*Soporte / Sottofondo / Podklad* **Double dossier /**  
*Action back*

**Jauge - Serrage (points) - Densité - NF ISO 1763**  
*Gauge - Rows (points) - Tufts*  
*Teilung - Stiche (points) - Noppenzahl* **5/64<sup>e</sup>**  
*Rijen - Deling (points) - Noppenaantal* **50 p**  
*Galga - Densidad (puntos)* **250 000 p/m²**  
*Scartamento - Serraggio (punti) - Densità felpa*  
*Zaciesnienie - Rozstaw igiel (punkty) - Gęstość*

**Comportement au feu Cfl-s1 - collé sur ciment**  
*Fire resistance Cfl-s1 - glued on cement*  
*Brennverhalten Cfl-s1 - geklebt auf Zement*  
*Brandgedrag Cfl-s1 - verlijmd op cement*  
*Clasificación al fuego Cfl-s1 - pegado en cemento*  
*Comportamento al fuoco Cfl-s1 - incollato su cemento*  
*Trudnozpalność Cfl-s1 - klejone na podłożu betonowym*



**Pose / Entretien / Traitement**  
*Laying / Cleaning / Treatment*  
*Verlegehinweis / Reinigung / Behandlung*  
*Plaatsinstructie / Reiniging / Onderhoud* **www.balsan.com**  
*Instalación / Mantenimiento / Tratamiento*  
*Posa / Manutenzione / Trattamenti*  
*Układanie / Utrzymanie w czystości / Impregnacja*

BALSAN se réserve le droit de modifier les caractéristiques de ce produit tout en conservant les mêmes qualités techniques. Dans le cadre d'une utilisation professionnelle, il est fortement conseillé d'utiliser des coloris moyens et foncés pour les pièces à grand trafic. De légères variations de coloris peuvent être observées entre les différents bains de teinture. / BALSAN reserves the right to modify the characteristics of this product while keeping the same technical properties. In the context of business use, we strongly recommend the use of darker colours for heavy traffic areas. Slight differences in colour may occur between different dye baths.



Designed and Made in France



Cachemire 740





wall to wall  
UNIS



wall to wall  
DESIGN



custom



modular



CAHIER TECHNIQUE  
TECHNICAL HANDBOOK

